

# Marshall Stability Apparatus - 1



## Purpose:

To find out the optimum bitumen content for a stable mix. The test is applicable to hot mix designs using bitumen and aggregates up to a maximum size of 25mm. In this method, the resistance to plastic deformation of cylindrical specimen of bituminous mixture is measured when the same is loaded at periphery at 5 cm per min.